



Tel: 866 765 9191  
 Fax: 717 261 9161  
 e-mail: sales@customizedcomponents.com  
 www.electricalinsulationmaterial.com  
 440 Ramsey Ave., Chambersburg, PA 17201

a broad range of products and services for OEM and contract manufacturers  
 a division of American Micro Industries, Inc.

## MATERIAL SPECIFICATION G10 / FR4

### General Description

G10/FR4 is a versatile, all-around electrically insulating material. G10 is an epoxy impregnated laminate which meets UL94-V0 requirements. G10 can be machined or die-cut to meet any custom requirement.

PROPERTIES	UNITS	VALUE
Tensile Strength	Lengthwise, psi	40,000
	Crosswise, psi	35,000
Compressive Strength	Flatwise, psi	60,000
	Edgewise, psi	35,000
Flexural Strength	Lengthwise, psi	55,000
	Edgewise, psi	45,000
Modulus of Elasticity in Flex	Lengthwise, psi x 10 <sup>6</sup>	2.7
	Crosswise, psi x 10 <sup>6</sup>	2.2
Shear Strength, psi		19,000
Izod Impact	Flatwise, ft/lb per inch of notch	7
	Edgewise, ft/lb per inch of notch	5.5
Rockwell Hardness M Scale		110
Specific Gravity		1.82
Coefficient of Thermal Expansion	Cm/cm deg C x 10 <sup>-5</sup>	.9
Water Absorption	0.062 in. thick, % per 24 hours	0.25
	0.125 in. thick, % per 24 hours	0.15
	0.500 in. thick, % per 24 hours	0.10
Dielectric Strength	0.062 in thick (perpendicular to laminations; short)	500
	0.125 in thick (perpendicular to laminations; short)	400
Dissipation Factor	Condition A, 1 megacycle	0.025
Dielectric Constant	Condition A, 1 megacycle	5.2
Insulation Resistance	Condition; 96 hrs at 90% relative humidity (mega ohms)	200,000
Flame Resistance	Underwriters Labs, Classification	94V-0
Bond Strength	lbs	2,000
Max Continuous Operating Temp.	Approximate degrees °F	285

The above information and data are believed to be accurate and reliable. American Micro Industries, Inc. assumes no responsibility for end-use applications and no performance warranty is expressed or implied.